


# Eastman G Maleated Polyolefins

## The Superior Coupling Additive for Fiberglass/Wollastonite<sup>a</sup> Reinforcement


Eastman G-3003 is a maleic-grafted polypropylene with optimum functionality and molecular weight developed to compatibilize glass fibers, wollastonite, and polypropylene. Addition of a small percentage of G-3003 (1%–5%) allows the substitution of up to 40% of the fiberglass with wollastonite to substantially lower the compound cost while improving or maintaining the same physical properties of non-coupled fiberglass-reinforced polypropylene.

The product can be added to the composite to aid not only in strengthening the composite, but also for composite processibility.

Eastman G-3003 polymer is available in 50 lb (22.7 kg) bags or 1,000 lb (453.6 kg) boxes. Bulk bag packaging or powder form is also available on a made-to-order basis.







30% Fiberglass/Wollastonite/PP



30% Fiberglass/Wollastonite/PP/Eastman

### Physical Data for 30% Fiberglass/Wollastonite-Reinforced Polypropylene



<sup>a</sup>Wollastonite supplied by NYCO Minerals, Inc.

# EASTMAN

## NORTH AMERICA

### Eastman Chemical Company Corporate Headquarters

P.O. Box 431  
Kingsport, TN 37662-5280 U.S.A.  
Telephone:  
U.S.A. and Canada, 800-EASTMAN (800-327-8626)  
Other Locations, (1) 423-229-2000  
Fax: (1) 423-229-1193  
www.eastman.com

## LATIN AMERICA

### Eastman Chemical Latin America

9155 South Dadeland Blvd.  
Suite 1116  
Miami, FL 33156 U.S.A.  
Telephone: (1) 305-671-2800  
Fax: (1) 305-671-2805

## EUROPE / MIDDLE EAST / AFRICA

### Eastman Chemical B.V.

Fascinatio Boulevard 602-614  
2909 VA Capelle aan den IJssel  
The Netherlands  
Telephone: (31) 10 2402 111  
Fax: (31) 10 2402 100  
www.tackifier.com

## ASIA PACIFIC

### Eastman (Shanghai) Chemical Commercial Company, Ltd. Jingan Branch

1206, CITIC Square  
N. 1168 Nanjing Road (W)  
Shanghai 200041, P. R. China  
Telephone: (86) 21 6120-8700  
Fax: (86) 21 5213-5255

### Eastman Chemical Japan Ltd.

AIG Aoyama Building 5F  
2-11-16 Minami Aoyama  
Minato-ku, Tokyo 107-0062 Japan  
Telephone: (81) 3-3475-9510  
Fax: (81) 3-3475-9515

### Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House  
3 Killiney Road  
Singapore 239519  
Telephone: (65) 6831-3100  
Fax: (65) 6732-4930

Eastman G™ polymers are products of Eastman Chemical Company and are protected under one or more of the following U.S. patents: 5,955,547; 6,046,279; 7,408,007; 7,683,134; and their foreign equivalents.

Material Safety Data Sheets providing safety precautions, that should be observed when handling and storing Eastman products, are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

*Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.*

Eastman G polymers are products of Eastman Chemical Company and are protected under one or more of the following U.S. patents: 5,955,547 and 6,046,279; and their foreign equivalents.

Eastman and Eastman G are trademarks of Eastman Chemical Company.

© Eastman Chemical Company, 2007.

Publication APG-4A  
May 2007

Printed in U.S.A.