


Eastman G Maleated Polyolefins

The Superior Coupling Additive for Talc Reinforcement


Eastman G-3003 is a maleic-grafted polypropylene with optimum functionality and molecular weight developed to compatibilize talc and polypropylene. Addition of a small percentage of G-3003 (1%–5%) results in a dramatic increase in tensile strength and other physical properties of talc-reinforced polypropylene composites.

The product can be added to the composite to aid not only in strengthening the composite, but also for composite processibility.

Eastman G-3003 polymer is available in 50 lb (22.7 kg) bags or 1,000 lb (453.6 kg) boxes. Bulk bag packaging or powder form is also available on a made-to-order basis.







20% Talc/PP



20% Talc/PP/*Eastman G*

Physical Data for 20% Talc/PP Composites





NORTH AMERICA

Eastman Chemical Company Corporate Headquarters

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

Telephone:
U.S.A. and Canada, 800-EASTMAN (800-327-8626)
Other Locations, (1) 423-229-2000
Fax: (1) 423-229-1193

www.eastman.com

LATIN AMERICA

Eastman Chemical Latin America

9155 South Dadeland Blvd.
Suite 1116
Miami, FL 33156 U.S.A.

Telephone: (1) 305-671-2800
Fax: (1) 305-671-2805

EUROPE / MIDDLE EAST / AFRICA

Eastman Chemical B.V.

Fascinatio Boulevard 602-614
2909 VA Capelle aan den IJssel
The Netherlands

Telephone: (31) 10 2402 111
Fax: (31) 10 2402 100

www.tackifier.com

ASIA PACIFIC

Eastman (Shanghai) Chemical Commercial Company, Ltd. Jingan Branch

1206, CITIC Square
N. 1168 Nanjing Road (W)
Shanghai 200041, P. R. China

Telephone: (86) 21 6120-8700
Fax: (86) 21 5213-5255

Eastman Chemical Japan Ltd.

AlG Aoyama Building 5F
2-11-16 Minami Aoyama
Minato-ku, Tokyo 107-0062 Japan

Telephone: (81) 3-3475-9510
Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House
3 Killiney Road
Singapore 239519

Telephone: (65) 6831-3100
Fax: (65) 6732-4930

Eastman G™ polymers are products of Eastman Chemical Company and are protected under one or more of the following U.S. patents: 5,955,547; 6,046,279; 7,408,007; 7,683,134; and their foreign equivalents.

Material Safety Data Sheets providing safety precautions, that should be observed when handling and storing Eastman products, are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Eastman G polymers are products of Eastman Chemical Company and are protected under one or more of the following U.S. patents: 5,955,547 and 6,046,279; and their foreign equivalents.

Eastman and Eastman G are trademarks of Eastman Chemical Company.

© Eastman Chemical Company, 2007.

Publication APG-5A
May 2007

Printed in U.S.A.