

Tips for Thermoforming
Eastar Copolyester 6763 Extruded Sheet

Introduction

Sheet extruded from *Eastar* copolyester 6763 is easy to thermoform if proper mold design, equipment, and operating techniques are employed. This brochure lists some helpful “tips” in processing *Eastar* copolyester 6763.

Mold Design

- To attain more consistent flange thicknesses, easier mold removal, reduced bridging (webbing) and reduced tray fracture issues, Eastman recommends using female molds with generous draft angles (minimum radius of $\frac{5}{64}$ inch [1.778 mm]). *Eastar* copolyester 6763 can be used successfully with male molds, but female molds enable more consistent flange thicknesses.
- To achieve proper forming, vacuum channels should lead directly from the inlets to the vacuum holes on the corners of the mold. Additionally, vacuum channels should always be clean.
- To achieve proper forming, minimize the use of right angles in the vacuum system and piping so vacuum speed is maximized and plastic contact with the mold is optimized.
- To prevent excess bridging (webbing) and flange thinning, use proper cavity spacing, especially on male tools. For every inch [25 mm] of depth into the mold cavity, there should be an inch [25 mm] of space between cavities.

Note: Mold shrinkage will vary depending upon the thermoforming process equipment configuration, but is typically 0.4 to 0.5 percent.

Thermoforming Process

- Eastman recommends starting with quality *Eastar* copolyester 6763 sheeting. Quality sheet is characterized as having consistent gauge, low contamination, low cosmetic defects, and consistent inherent viscosity or molecular weight.
- Denesting must be augmented for easy blister removal from a stack prior to product insertion on some tray designs.
 - Silicone-coated sheet is often used to optimize denesting of blisters. Eastman suggests using *Dow Corning* 365 silicone.
 - When silicone coating is not permitted, an internal denest can be blended with *Eastar* copolyester 6763. *Eastar* copolyester 6763 C0030 denest is a denest concentrate recommended and offered by Eastman. It is typically blended with *Eastar* copolyester 6763 at a ratio of 50:1 to 100:1.
- The mold surface should maintain a consistent temperature of 100°F (40°C) to 140°F (60°C) to prevent chill line formation or sticking.

- Heat settings on thermoforming equipment should be adjusted to produce the highest possible sheet temperature without sticking or bridging. For *Eastar* copolyester 6763, the optimum sheet temperature range for thermoforming is 280°F (140°C) to 300°F (150°C). Higher sheet temperatures can result in final thermoformed packages with lower internal stress. In addition, overheating film and sheet will cause the sheet to sag resulting in bridging (webbing) in the final thermoformed package. The degree of sheet sag is directly proportional to the combined effects of oven temperature and the sheet dwell time in the oven. Decreasing oven dwell time while increasing oven temperature allows higher sheet temperatures without excess sagging. Decreasing the oven dwell time has the added benefit of decreasing cycle times. This also enables the use of smaller ovens on the thermoforming machine decreasing energy needs and the process footprint.
- For blank-fed male mold thermoforming machines, forming can be improved and bridging can be decreased or eliminated by using wire-helper grids.
- Internal stresses should be monitored using a polarized light table.

Cutting Sheet

- Sharp, properly guarded and well-maintained steel cutters are required for proper cutting of formed parts. The cutters can be of the rule, roller-die, matched-die, slitter, or guillotine design.
- Proper clearance between punch and die (usually zero) should be maintained with matched-die cutters.
- Double-bevel die stock measuring 3-point, 0.042 inch (1.1 mm), with a Rockwell C hardness of 50 to 55 is suggested when cutting simple-shaped blisters.
- Complex-shaped blisters should be cut with double-bevel die stock measuring 3-point, 0.042 inch (1.1 mm), with a Rockwell C hardness of 45 to 50.
- Blisters of *Eastar* copolyester 6763 should be cut through completely when using steel-rule cutting. The cutting stroke on the trim press should stop just after cutting through the blister. This is known as a “kiss” cut.
- Stainless steel striker plates 0.125 inch (3.2 mm) thick with an equivalent or slightly softer hardness than the die material is recommended.
- Heated steel-rule knives can often improve the quality of the cut.
- Dies should have steel backup plates with a thickness of 0.030 inch (0.80 mm).
- Backup plates should be made of metal with a Rockwell C hardness of 30 to 35.

Eastman recommends following these tips to fully experience the benefits of easy thermoforming with *Eastar* copolyester 6763 on a consistent basis.

EASTMAN

■ NORTH AMERICA

Eastman Chemical Company Corporate Headquarters

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

Telephone:
U.S.A. and Canada, 800-EASTMAN (800-327-8626)
Other Locations, (1) 423-229-2000
Fax: (1) 423-229-1193
www.eastman.com

■ LATIN AMERICA

Eastman Chemical Latin America

9155 South Dadeland Blvd.
Suite 1116
Miami, FL 33156 U.S.A.

Telephone: (1) 305-671-2800
Fax: (1) 305-671-2805

■ EUROPE / MIDDLE EAST / AFRICA

Eastman Chemical B.V.

Fascinatio Boulevard 602-614
2909 VA Capelle aan den IJssel
The Netherlands

Telephone: (31) 10 2402 111
Fax: (31) 10 2402 100

■ ASIA PACIFIC

Eastman (Shanghai) Chemical Commercial Company, Ltd. Jingan Branch

1206, CITIC Square
No. 1168 Nanjing Road (W)
Shanghai 200041, P.R. China

Telephone: (86) 21 6120-8700
Fax: (86) 21 5213-5255

Eastman Chemical Japan Ltd.

AIG Aoyama Building 5F
2-11-16 Minami Aoyama
Minato-ku, Tokyo 107-0062 Japan

Telephone: (81) 3-3475-9510
Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House
3 Killiney Road
Singapore 239519

Telephone: (65) 6831-3100
Fax: (65) 6732-4930

Material Safety Data Sheets providing safety precautions, that should be observed when handling and storing *Eastman* products, are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not *Eastman* products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

It is the responsibility of the medical device manufacturer ("Manufacturer") to determine the suitability of all component parts and raw materials, including any Eastman product, used in its final product in order to ensure safety and compliance with requirements of the United States Food and Drug Administration (FDA) or other international regulatory agencies.

Eastman products have not been designed for nor are they promoted for end uses that would be categorized either by the United States FDA or by the International Standards Organization (ISO) as implant devices. Eastman products are not intended for use in the following applications: (1) in any bodily implant applications for greater than 30 days, based on FDA-Modified ISO-10993, Part 1, "Biological Evaluation of Medical Devices" tests (including any cosmetic, reconstructive, or reproductive implant applications); (2) in any cardiac prosthetic device application, regardless of the length of time involved, including, without limitation, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass assisted devices; or (3) as any critical component in any medical device that supports or sustains human life.

For manufacturers of medical devices, biological evaluation of medical devices is performed to determine the potential toxicity resulting from contact of the component materials of the device with the body. The ranges of tests under FDA-Modified ISO-10993, Part 1, "Biological Evaluation of Medical Devices" include cytotoxicity, sensitization, irritation or intracutaneous reactivity, systemic toxicity (acute), subchronic toxicity (sub-acute), implantation, and hemocompatibility. For Eastman products offered for the medical market, limited testing information is available upon request. The Manufacturer of the medical device is responsible for the biological evaluation of the finished medical device.

The suitability of an Eastman product in a given end-use environment is dependent upon various conditions including, without limitation, chemical compatibility, temperature, part design, sterilization method, residual stresses, and external loads. It is the responsibility of the Manufacturer to evaluate its final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Eastar is a trademark of Eastman Chemical Company.

© Eastman Chemical Company, 2007.