

Eastman™ Adhesion Promoters Technical Tip

Compatibility of Eastman™ Waterborne Polyolefins and European Resins (TT-36C)

INTRODUCTION

Applying paint to polypropylene and other thermoplastic polyolefins (TPO) is difficult because most coatings exhibit poor adhesion to these types of plastics. Eastman™ chlorinated polyolefin (CPO) adhesion promoters are an effective tool for improving paint adhesion to these substrates and are now supplemented by Eastman Advantis™ 510W, a new waterborne chlorine-free adhesion promoter. The addition of Eastman™ polyolefin dispersions to waterborne systems provides a means to promote adhesion and makes it possible to apply an adhesion promoting primer.

The purpose of this technical tip is to indicate to customers which resins are compatible or likely to be compatible with Eastman™ waterborne PO materials. Furthermore, a short study was performed to demonstrate the improved adhesion of both an acrylic and

polyurethane dispersion onto a TPO substrate by direct addition of the adhesion promoters prior to spray application.

The information in this technical tip will be of interest to customers involved in the production of coatings for low surface energy plastic substrates for automotive, teletronics, printing inks, or general industrial applications.

DISCUSSION

Physical Properties

Eastman™ CP 310W, CP 347W, and CP 349W waterborne chlorinated polyolefin adhesion promoters, water dispersions of the same CPO resin, differ in the neutralizing amine in each and the presence of ethylene glycol in Eastman™ CP 349W. Eastman Advantis™ 510W is the next generation waterborne, halogen-free polyolefin adhesion promoter. The physical properties of each are shown in Table 1.

Table 1: Typical Properties^a

Typical Properties	Eastman™ CP 310W	Eastman™ CP 347W	Eastman™ CP 349W	Eastman Advantis™ 510W
Weight % solids	30	25	26	24
Weight % CPO	24	20	20	—
Solvent	—	—	5% ethylene glycol	—
pH @ 25%	9–10	9–10	9–10	8
Stability Shelf, 1 year	No change	No change	No change	No significant change
50°C, 4 week	Slight settle	No change	No change	No significant change
Freeze/thaw	Good	Good	Good	Poor

^aEastman makes no representation that product in any particular shipment will conform exactly to the values listed.

Compatibility of Eastman™ Waterborne Polyolefins and European Resins (TT-36C)

Generally, the faster-evaporating ammonia in Eastman™ CP 310W makes it more useful in adhesion promoting primers that are air-dried before application of the topcoat. The 2-amino-2-methyl-1-propanol in Eastman™ CP 347W and CP 349W make them more compatible with other waterborne resins and therefore more useful as additives. However, there are exceptions to these generalizations, depending on the other components of the substrate/coating system.

Compatibility with European Resins

Eastman™ adhesion promoter dispersions can be added directly to waterborne coating formulations to improve adhesion to polypropylene-based substrates. The utilization

of adhesion promoters and resin blends depends initially on the compatibility of the waterborne PO (WBPO) with the water-based resin. The data in Table 2 illustrates the compatibility of Eastman™ adhesion promoters with various coating resins available in Europe. Details of the resin types and manufacturers used in this study are found on the final page of this technical tip.

The adhesion promoters were added to the resin systems at 10%, 20% and 30% levels (wt./wt. on resin solids). In some instances, the addition of (a) 2-butoxyethanol or (b) Eastman Texanol™ EA was required to produce an acceptable coalesced film. The compatibility was assessed by visually checking the solution and the appearance of the dry film on glass. The results of the compatibility study are shown in Table 2.

Table 2: Compatibility Data

Resin	Coalescent Level	Adhesion Promoter Addition Level Percentage												
		Eastman™ CP 310W			Eastman™ CP 347W			Eastman™ CP 349W			Eastman Advantis™ 510W			
		10%	20%	30%	10%	20%	30%	10%	20%	30%	10%	20%	30%	
AS2605	20% ^a	SI	SI	SI	SI	SI	SI	SI	SI	SI	SI	I	I	I
AS2610	30% ^a	I	I	I	I	I	I	I	I	I	I	I	I	I
AS2615	20% ^a	C	C	C	C	C	C	C	C	C	C	SI*	VSI	C
CUR99	—	C	C	C	C	C	C	C	C	C	C	C	C	C
Lux101	—	C	C	C	C	C	C	C	C	C	C	C	C	C*
Lux352	—	C	C	C	C	C	C	C	C	C	C	C	C	C*
Lux399	—	C*	C*	C*	C*	C*	C*	C*	C*	C*	C*	C	C	C*
U325	—	C	C	C	C	C	C	C	C	C	C	C	C	C
U615	—	C	C	C	C	C	C	C	C	C	C	C	C	C
Bayhydrol A145	—	C	C	C	C	C	C	C	C	C	C	C	C	C
Bayhydrol PT241	—	C*	VSI*	SI	C	C	C	C	C	C	C	VSI	SI	SI
Bayhydrol VPLS 2139	—	I	I	I	SI	SI	SI	SI	SI	SI	SI	SI*	SG	SG
Bayhydrol VPLS 2290	—	C*	C	C	C*	C	C	C*	C	C	C	I	I	I
Bayhydrol VPLS2952	—	VSI	VSI	SI	C	C	C	C	C	C	C	VSI	VSI	VSI
Neocryl A615	—	C	C	SI	C	C	VSI	C	C	C	C	C	C	C
Neocryl A639	20% ^a	SI	SI	SI	SI	SI	SI	VSI	SI	SI	SI	VSI*	VSI*	VSI*

^a2-Butoxyethanol, ^bEastman Texanol™ ester alcohol

C = Compatible, I = Incompatible, SG = Solution gelled, SI = Slightly incompatible, VSI = Very slightly incompatible, * = Solution viscosity increase

Compatibility of Eastman™ Waterborne Polyolefins and European Resins (TT-36C)

Table 2: Compatibility Data, cont.

Resin	Coalescent Level	Adhesion Promoter Addition Level Percentage											
		Eastman™ CP 310W			Eastman™ CP 347W			Eastman™ CP 349W			Eastman™ Advantis™ 510W		
		10%	20%	30%	10%	20%	30%	10%	20%	30%	10%	20%	30%
<i>Neocryl A662</i>	20% ^a	VSI	VSI	SI	C	C	C	C	C	C	I	I	I
<i>Neocryl XK12</i>	10% ^a	I	I	I	I	I	I	I	I	I	C	C	C
<i>Neocryl XK62</i>	10% ^a	C	C	C	C	C	C	C	C	C	C	C	C
<i>Incorez W830/140</i>	—	C	C	C	C	C	C	C	C	C	C	C	C
<i>Incorez W835/177</i>	—	C	C	C	C	C	C	C	C	C	C	C	C
<i>Incorez W830/397</i>	—	SI	SI	SI	SG	SG	SG	SG	SG	SG	SI*	SI*	SI*
<i>Incorez W830/446</i>	—	C	C	C	C	C	C	C	C	C	C	C	C
<i>Incorez W2310</i>	—	I	I	I	I	I	I	I	I	I	I	I	I
<i>Incorez W2450</i>	—	C	C	C*	C	C	C	C	C	C	C	C	C
<i>Incorez W2600</i>	—	VSI	VSI	VSI	VSI	VSI	VSI	VSI	VSI	VSI	C	C	C
<i>Joncryl 1555</i>	—	VSI*	SG	SG	C	SG	SG	C	SG	SG	C	C	C
<i>Joncryl 8211</i>	15% ^b	SG	SG	SG	SI*	SG	SG	SI*	SG	SG	C	VSI*	VSI*
<i>Joncryl 8320</i>	10% ^b	SG	SG	SG	VSI*	VSI*	VSI*	VSI*	VSI*	VSI*	C*	C*	VSI*
<i>Joncryl 8330</i>	10% ^a	C	VSI*	I	C	C	C	C	C	C	C	C	C
<i>Setal 6306 SS60</i>	—	SG	SG	SG	SG	SG	SG	SG	SG	SG	SG	SG	SG
<i>Setalux 6510 AQ42</i>	—	C	C	C	C	C	C	C	C	C	C	C	C
<i>Setalux 6511 AQ47</i>	—	C*	I	I	C	C	C	C	C	C	C	C	C
<i>Setalux 6520 AQ45</i>	10% ^a	VSI	SI	SI	VSI	SI	SI	VSI	VSI	SI	I	I	I
<i>Setalux 6758 AQ40</i>	—	C	C	C	C	C	C	C	C	C	C	C	C
<i>Setalux 6801 AQ24</i>	—	SG	SG	SG	C*	SG	SG	C*	SG	SG	SG	SG	SG
<i>Primal AC339</i>	10% ^a	SI	SI	SI	VSI	VSI	VSI	C	C	C	C	C	C
<i>Primal WL100</i>	10% ^a	VSI	VSI	VSI	C	C	C	C	C	C	C	C	C
<i>Primal WL91K</i>	10% ^a	VSI	VSI	VSI	C	C	C	C	C	C	C	C	C

^a2-Butoxyethanol, ^bEastman Texanol™ ester alcohol

C = Compatible, I = Incompatible, SG = Solution gelled, SI = Slightly incompatible, VSI = Very slightly incompatible, * = Solution viscosity increase

Compatibility of Eastman™ Waterborne Polyolefins and European Resins (TT-36C)

Adhesion Performance

To indicate the adhesion performance of coatings applied to polypropylene, a series of clear (non-pigmented) primers was prepared using Eastman Advantis™ 510W blended with a polyurethane dispersion and a styrene-acrylic emulsion.

Co-resins tested:

Incorez W835/177:

Co-solvent free polyurethane dispersion (PUD)

Neorez XK62:

Styrene-acrylic emulsion

The primer coats were spray applied onto *Sabic* PP108MF97 (PP/EPDM) substrate, then overcoated with a solventborne silver metallic basecoat and 2K acrylic/urethane clearcoat. A cross-hatch adhesion test was performed after 24 hours. Applying and removing tape over the scribed cross-hatch test area measured the amount of coating left on substrate (0% = worst adhesion, 100% = best adhesion). The results shown in Table 3 indicate that the addition of Advantis™ 510W to both the acrylic and PUD improved the adhesion to the substrate from poor to excellent.

Paint Application

Primer:

Pneumatic spray (5bar) to 4µm DFT (Dry Film Thickness). 30 minutes flash-off

Basecoat:

Pneumatic spray (4bar) to 15µm DFT. 10 minutes flash-off

2K Clearcoat:

Pneumatic spray (4bar) to 35µm DFT. 10 minutes flash-off

Cure time:

20 minute @ 80°C

Use in Adhesion-Promoting Primers

Eastman™ adhesion promoter dispersions are used as the base resin in adhesion-promoting primers. Information on optimization for this application is available in Eastman publication GN-411, *Formulating with Eastman™ Waterborne CPO Adhesion Promoters*.

CONCLUSION

This study clearly indicates the versatility of Eastman™ waterborne polyolefin adhesion promoters for use in combination with European resin dispersions. It further illustrates how the addition of a WBPO to examples of such dispersions resulted in improved adhesion on a polyolefin-based substrate. Additionally, Advantis™ 510W provides the advantage of being halogen-free benefiting the user by reducing environmental issues with regards to waste paint disposal and recycling of coated parts. For additional information or for help in determining which Eastman™ waterborne polyolefin adhesion promoter best suits your application, please contact Eastman Technical Service.

Table 3: Adhesion Data

Film Former	<i>Neocryl</i> XK62 - Acrylic			<i>Incorez</i> W835/177 - PUD		
	None	Eastman Advantis™ 510W		None	Eastman Advantis™ 510W	
Adpro : Film former (on solids):	N/A	25:75	50:50	N/A	25:75	50:50
Cross-hatch adhesion After 24 hours	0%	100%	100%	0%	100%	100%

Compatibility of Eastman™ Waterborne Polyolefins and European Resins (TT-36C)

Manufacturer and Resin Type

Product	Manufacturer	Type	% Solid
AS2605	Alberdingk Boley	Styrene acrylic	50
AS2610	Alberdingk Boley	Styrene acrylic	50
AS2615	Alberdingk Boley	Styrene acrylic	51
CUR99	Alberdingk Boley	PUD	30
Lux101	Alberdingk Boley	UV cure polyester PUD	40
Lux352	Alberdingk Boley	UV cure acrylic co-polymer	43
Lux399	Alberdingk Boley	UV cure polyester PUD acrylic co-polymer	45
U325	Alberdingk Boley	PUD	40
U615	Alberdingk Boley	PUD	39
Bayhydrol A145	Bayer	Acrylic polyol	45
Bayhydrol PT241	Bayer	Polyester PUD	41
Bayhydrol VPLS 2139	Bayer	Polyester/polyacrylate polyol	48
Bayhydrol VPLS 2290	Bayer	Polyester/polyacrylate dispersion	45
Bayhydrol VPLS2952	Bayer	PUD	40
Neocryl A615	DSM Neoresins	Acrylic dispersion	36
Neocryl A639	DSM Neoresins	Acrylic emulsion	45
Neocryl A662	DSM Neoresins	Acrylic emulsion	40
Neocryl XK12	DSM Neoresins	Acrylic emulsion	45
Neocryl XK62	DSM Neoresins	Styrene acrylic	42
Incorez W830/140	Industrial Copolymers Ltd	Polycarbonate PUD	32
Incorez W835/177	Industrial Copolymers Ltd	Polyester PUD	34
Incorez W830/397	Industrial Copolymers Ltd	Polyester PUD	33
Incorez W830/446	Industrial Copolymers Ltd	PUD	34
Incorez W2310	Industrial Copolymers Ltd	Urethane/acrylic hybrid	38
Incorez W2450	Industrial Copolymers Ltd	Urethane/acrylic hybrid	40
Incorez W2600	Industrial Copolymers Ltd	Urethane/acrylic hybrid	40
Joncryl 1555	Johnson Polymer	Acrylic emulsion	45
Joncryl 8211	Johnson Polymer	Acrylic emulsion	44
Joncryl 8320	Johnson Polymer	Acrylic emulsion	41
Joncryl 8330	Johnson Polymer	Acrylic emulsion	38
Setalux 6306 SS60	Nuplex Resins	Polyester polyol	60
Setalux 6510 AQ42	Nuplex Resins	Acrylic polyol	42
Setalux 6511 AQ47	Nuplex Resins	Acrylic polyol	47
Setalux 6520 AQ45	Nuplex Resins	Acrylic polyol	45
Setalux 6758 AQ40	Nuplex Resins	Acrylic dispersion	40
Setalux 6801 AQ24	Nuplex Resins	Acrylic co-polymer	24
Primal AC339	Rohm & Haas	Acrylic co-polymer	48
Primal WL100	Rohm & Haas	Acrylic co-polymer	50
Primal WL91K	Rohm & Haas	Acrylic co-polymer	40.5

Eastman™ Adhesion Promoters Technical

TT-36C

EASTMAN

NORTH AMERICA

Eastman Chemical Company Corporate Headquarters

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

Telephone:

U.S.A. and Canada, 800-EASTMAN (800-327-8626)

Other Locations, (1) 423-229-2000

Fax: (1) 423-229-1193

www.eastman.com

LATIN AMERICA

Eastman Chemical Latin America

9155 South Dadeland Blvd.

Suite 1116

Miami, FL 33156 U.S.A.

Telephone: (1) 305-671-2800

Fax: (1) 305-671-2805

EUROPE / MIDDLE EAST / AFRICA

Eastman Chemical B.V.

Fascinatio Boulevard 602-614

2909 VA Capelle aan den IJssel

The Netherlands

Telephone: (31) 10 2402 111

Fax: (31) 10 2402 100

ASIA PACIFIC

Eastman (Shanghai) Chemical Commercial Company, Ltd. Jingan Branch

1206, CITIC Square

No. 1168 Nanjing Road (W)

Shanghai 200041, P.R. China

Telephone: (86) 21 6120-8700

Fax: (86) 21 5213-5255

Eastman Chemical Japan, Ltd.

AIG Aoyama Building 5F

2-11-16 Minami Aoyama

Minato-ku, Tokyo 107-0062 Japan

Telephone: (81) 3-3475-9510

Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House

3 Killiney Road

Singapore 239519

Telephone: (65) 6831-3100

Fax: (65) 6732-4930

Material Safety Data Sheets providing safety precautions, that should be observed when handling and storing Eastman products, are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Advantis, Eastman, and Texanol are trademarks of Eastman Chemical Company.

© Eastman Chemical Company, 2007.

Publication TT-36C
September 2007