

EASTMAN

Eastman™ hydrocarbon resins

For adhesive applications



The results of insight™

Eastman™ hydrocarbon resins

Resin tradename	RBSP (°C) ¹	T _g (°C) ²	Color (Gardner) ³	Mol. wt. (Mz) ⁴	MMAP (°C) ⁵
Aliphatic					
Regalrez™ 1018	liquid	-22	<1	500	64
Regalrez™ 1094	95	40	<1	1,350	84
Regalrez™ 1085	87	34	<1	1,500	87
Regalrez™ 1126	124	67	<1	2,050	92
Regalrez™ 1128	130	72	<1	3,900	104
Regalrez™ 1139	141	84	<1	5,200	109
Regalite™ R1010	liquid	nm ⁶	na ⁷	na ⁷	82
Regalite™ R1090	88	36	<1	1,100	74
Regalite™ S1100	100	na ⁷	<1	1,300	77
Regalite™ R1100	100	50	<1	1,500	78
Regalite™ R1125	123	70	<1	2,100	86
Plastolyn™ R1140	140	84	<1	2,400	93
Eastotac™ H-100W	100	41	<1	2,150	81
Eastotac™ H-115W	115	56	<1	2,100	80
Eastotac™ H-130W	130	78	<1	2,200	83
Eastotac™ H-142W	142	88	<1	2,200	85
Eastotac™ H-100L	100	44	<1	2,300	78
Eastotac™ H-130L	130	75	<1	2,350	83
Eastotac™ H-115L	115	60	<1	2,400	82
Eastotac™ H-115R	115	53	2	2,450	82
Eastotac™ H-100R	100	44	2	2,550	79
Eastotac™ H-142R	142	87	2	2,300	82
Eastotac™ H-130R	130	73	2	2,400	84
Eastotac™ H-100E	100	44	5	2,450	77
Eastotac™ H-115E	115	61	5	2,600	80
Eastotac™ H-130E	130	66	5	2,350	78
Piccotac™ 1020	liquid	nm ⁶	3	2,600	92
Piccotac™ 1094-E	95	nd	5	3,400	89
Piccotac™ 1095	96	43	3	3,500	94
Piccotac™ 1095-N	96	nd ⁸	3	3,600	94
Piccotac™ 1098	100	47	3	4,950	94
Piccotac™ 1100-N	99	nd	3	7,000	na ⁷
Piccotac™ 1100	101	46	3	8,250	96
Piccotac™ 1100E-RM	100	nd ⁸	4	6,800	92
Piccotac™ 1105-E	101	nd ⁸	4	8,800	97
Piccotac™ 1115	112	58	4	10,500	99
Piccotac™ 1100-E	99	nd ⁸	5	6,800	96
Aliphatic/Aromatic					
Regalite™ R9100	99	50	<1	1,300	72
Regalite™ S7125	123	nd ⁸	<1	2,200	75
Regalite™ R7100	102	49	<1	1,500	63
Regalite™ S5100	97	50	<1	1,600	58
Regalrez™ 6108	108	55	<1	2,300	53
Regalrez™ 3102	102	51	<1	2,350	24
Piccotac™ 9095	94	42	3	4,200	88
Piccotac™ 9105	105	52	2	9,750	92
Piccotac™ 8595	95	44	na ⁷	3,200	81
Piccotac™ 8095	95	41	3	5,500	76
Piccotac™ 8090-E	92	nd ⁸	4	3,800	64
Piccotac™ 7050	50	7	3	1,730	65
Piccotac™ 7590-N	91	39	2	2,500	62
Piccotac™ 6095-E	98	45	7	4,000	35
Picco™ AR85	87	na ⁷	9	1,090	na ⁷
Picco™ AR100	100	na ⁷	8	1,200	na ⁷
Picco™ 2215	113	55	12	3,500	45
Aromatic					
Endex™ 155	153	99	<1	13,850	16
Endex™ 160	159	105	<1	18,400	16
Kristalex™ 1120	119	60	<1	7,600	5
Kristalex™ 3070	70	32	<1	1,450	0
Kristalex™ 3085	85	41	<1	1,900	1
Kristalex™ 3100	100	53	<1	2,550	5
Kristalex™ 3115	115	nd ⁸	<1	3,700	3
Kristalex™ 5140	139	85	<1	12,100	9
Kristalex™ F85	86	nd ⁸	<1	1,950	1
Kristalex™ F100	99	53	<1	2,200	2
Kristalex™ F115	117	nd ⁸	<1	3,300	2
Piccotex™ 75	75	32	<1	1,700	1
Piccotex™ 100	98	50	<1	3,600	7
Piccotex™ 120	118	70	<1	6,400	11
Piccotex™ LC	91	46	<1	2,200	3
Plastolyn™ 240	121	43	<1	8,500	8
Plastolyn™ 290	140	84	<1	16,000	9
Piccolastic™ A5	liquid	nm ⁶	2	550	-6
Piccolastic™ A75	74	35	1	2,250	6
Piccolastic™ D125	126	64	2	200,000	13
Picco™ A10	liquid	nd ⁸	9	1,850	na ⁷
Picco™ A100	101	nd ⁸	9	2,200	6
Picco™ A120	125	nd ⁸	8	2,600	na ⁷
Picco™ A140	142	nd ⁸	8	3,200	na ⁷
Picco™ 6100	102	46	11	5,300	30
Picco™ 5120	120	60	12	5,300	23
Picco™ 5140	140	84	12	6,000	23
Picco™ 2100	102	43	12	3,600	34
Picco™ B100	100	nd ⁸	13	na ⁷	na ⁷



¹Ring & Ball Softening Point, ASTM Method E-28

²Glass Transition temperature by differential scanning calorimetry

³Color, Gardner method, 50% in toluene, ASTM D6166

⁴Molecular Weight, Z-average, from gel permeation chromatography, elution with THF

⁵Cloud Point temperature from 2:1 Vol:Vol aniline methyl cyclohexane, Eastman Method

⁶Not measurable—transition not detected

⁷Not available

⁸Not determined

EASTMAN

Eastman Chemical Company Corporate Headquarters

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

Telephone:
U.S.A. and Canada, 800-EASTMAN (800-327-8626)
Other Locations, (1) 423-229-2000
Fax: (1) 423-229-1193

Eastman Chemical Latin America

9155 South Dadeland Blvd.
Suite 1116
Miami, FL 33156 U.S.A.

Telephone: (1) 305-671-2800
Fax: (1) 305-671-2805

Eastman Chemical B.V.

Fascinatio Boulevard 602-614
2909 VA Capelle aan den IJssel
The Netherlands

Telephone: (31) 10 2402 111
Fax: (31) 10 2402 100

Eastman (Shanghai) Chemical Commercial Company, Ltd. Jingan Branch

1206, CITIC Square
No. 1168 Nanjing Road (W)
Shanghai 200041, P.R. China

Telephone: (86) 21 6120-8700
Fax: (86) 21 5213-5255

Eastman Chemical Japan Ltd.

AIG Aoyama Building 5F
2-11-16 Minami Aoyama
Minato-ku, Tokyo 107-0062 Japan

Telephone: (81) 3-3475-9510
Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House
3 Killiney Road
Singapore 239519

Telephone: (65) 6831-3100
Fax: (65) 6732-4930

www.eastman.com

Material Safety Data Sheets providing safety precautions, that should be observed when handling and storing Eastman products, are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Eastman, Eastotac, Endex, Kristalex, Picco, Piccolastic, Piccotac, Piccotex, Plastolyn, Regalite, Regalrez, and The results of insight are trademarks of Eastman Chemical Company.

© Eastman Chemical Company, 2011.