

Pamolyn™ Tall Oil Fatty Acids

Pamolyn™ fatty acids are low in odor, range in color from water-white to pale yellow, and have excellent color stability. They are primarily oleic and linoleic acids.

Pamolyn™ 100 is unique among commercial fatty acids for its high oleic content. The unique refining process results in very low levels of rosin acids, α -linolenic acid and is also low in saturated fatty acids and unsaponifiables.

Pamolyn™ 100 FGK has the same high oleic acid content as Pamolyn™ 100 and is food-grade and kosher-certified.

Pamolyn™ 200 is a high purity grade of linoleic acid especially designed for the protective coatings industry. Because of the near absence of saturated fatty acids, this product has exceptionally low titer.

Pamolyn™ 300 fatty acid is a conjugated linoleic and linoleic acid-rich blend. Outstanding for low odor, pale color, and color stability, Pamolyn™ 300 fatty acid contains 38 to 42% conjugated diene fatty acids.

Pamolyn™ 327B is a partially bodied fatty-acid blend designed to be a direct replacement for dehydrated castor oil.

Pamolyn™ 380 conjugated linoleic acid is especially useful for production of chemical intermediates by Diels-Alder chemistry.

This broad range of properties accounts for a wide diversity of end-use applications.

Typical uses for Pamolyn™ fatty acids

- Chemical intermediates
- Synthetic detergents
- Plasticizers
- Emulsifiers
- Defoamers
- Lubricants
- Epoxy resin esters
- Alkyds and other protective coating resins

Typical composition Pamolyn™ fatty acids

Product family	Grade	Oleic acid, %	Linoleic acids, %	Conjugated linoleic acids, %	Linolenic acids, %	Saturated fatty acids, %	Rosin acids, %	Unsaponifiabiles, %	Acid Number (mg KOH/100g)
Pamolyn™ oleic acids	100	89	7	1.5	0.1	3	nil	0.3	198
	100FGK	90	6	1.5	0.1	3	nil	0.3	198
	125	84	12	2.5	0.3	3	0.2	0.4	198
	150	77	18	4	0.8	3.5	0.4	0.6	196
Pamolyn™ linoleic acids	200	21	74	11	4	1	1.5	2.5	193
	210	21	73	11	4	1	1.5	2.7	193
Pamolyn™ Conjugated linoleic acid	380	22	74	68	3	1	1.5	2.6	195
Pamolyn™ fatty acid blends	240	31	63	9	4	1.5	1.3	2.2	193
	300	21.5	74	39	3.3	1	1.5	2.6	192
	327B	20	75	27	3	1	1.4	2.3	192
	347	45	51	40	2	2	0.9	1.6	194
	CB-70	65	29	6	2	3	2.9	1.3	195
Pamolyn™ saturates		40	40	7	2	17	0.8	1.6	192

The values presented in this brochure are average values and should not be construed as product specifications. Please refer to *Pamolyn Overview and Sales Specifications*.

EASTMAN

Eastman Chemical Company Corporate Headquarters

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

Telephone:
U.S.A. and Canada, 800-EASTMAN
(800-327-8626)
Other Locations, (1) 423-229-2000
Fax: (1) 423-229-1193

Eastman Chemical Latin America

9155 South Dadeland Blvd.
Suite 1116
Miami, FL 33156 U.S.A.

Telephone: (1) 305-671-2800
Fax: (1) 305-671-2805

Eastman Chemical B.V.

Fascinatio Boulevard 602-614
2909 VA Capelle aan den IJssel
The Netherlands

Telephone: (31) 10 2402 111
Fax: (31) 10 2402 100

Eastman (Shanghai) Chemical Commercial Company, Ltd. Jingan Branch

1206, CITIC Square
No. 1168 Nanjing Road (W)
Shanghai 200041, P.R. China

Telephone: (86) 21 6120-8700
Fax: (86) 21 5213-5255

Eastman Chemical Japan, Ltd.

AIG Aoyama Building 5F
2-11-16 Minami Aoyama
Minato-ku, Tokyo 107-0062 Japan

Telephone: (81) 3-3475-9510
Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House
3 Killiney Road
Singapore 239519

Telephone: (65) 6831-3100
Fax: (65) 6732-4930

www.eastman.com

Material Safety Data Sheets providing safety precautions, that should be observed when handling and storing Eastman products, are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Eastman and Pamolyn are trademarks of Eastman Chemical Company.

© Eastman Chemical Company, 2008.