

# Material selector guide

Injection molding for  
the personal care market



# Material selector guide

## Injection molding for the personal care market

Product	Appearance/ finish	Specific gravity ASTM D792	Deflection temperature °C (°F) ASTM D648		Optical properties ASTM D1003		Flexural modulus MPa (10 <sup>5</sup> psi) ASTM D790
			@ 1.82 MPa (264 psi)	@ 0.455 MPa (66 psi)	Transmittance %	Haze %	
Estar™ copolyesters							0.125 in. thickness
CN005	Clear transparent, high gloss	1.20	63 (145)	71 (160)	90	<0.60	1,800 (2.6)
EB062		1.25	63 (145)	73 (163)	91	1.30	1,900 (2.7)
EN067		1.32	61 (142)	66 (151)	84	—	2,600 (3.8)
GN007 <sup>a</sup>		1.27	62 (143)	70 (158)	90	0.2	2,060 (3.0)
GN071 <sup>a</sup>		1.27	66 (150)	70 (158)	90	0.2	2,060 (3.0)
5011 <sup>a</sup>		1.28	62 (143)	67 (152)	85	0.3	2,200 (3.2)
DN011	Clear transparent, high gloss	1.23	64 (147)	73 (163)	92	<1.00	1,800 (2.6)
AN004		1.20	65 (149)	73 (164)	91	0.3	2,000 (2.9)
AN014		1.19	66 (150)	73 (163)	92	<1.00	1,900 (2.7)
EN076		1.32	62 (144)	69 (156)	89	0.8	2,350 (3.4)
Eastman Cristal™ copolyester							
Cristal 400	Extremely clear, high gloss	1.28	61 (142)	68 (155)	92	0.24	1,810 (2.6)
Eastman Tritan™ copolyesters							
LX101	Clear transparent, high gloss	1.18	99 (210)	85 (185)	90	<1.00	1,550 (2.25)
LX151HF		1.18	81 (178)	94 (201)	91	<1.00	1,575 (2.8)
LX201		1.17	92 (198)	109 (228)	92	<1.00	1,585 (2.28)

<sup>a</sup>Data are based on limited testing.

<sup>b</sup>Nonbreak as defined in ASTM D256 using 854 J/m (16 ft·lbf/in.) capacity pendulum with 3.2-mm (1/8-in.) specimens.

Unless noted otherwise, all tests were run @ 23°C (73°F) and 50% relative humidity.

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Conversions of metric/U.S. customary values may have been rounded off and therefore may not be exact conversions.

Rockwell hardness (R Scale) ASTM D785	Notched Izod impact @ 23°C (73°F) J/m (ft•lbf/in.) ASTM D256	Tensile yield ASTM D638		Tensile break ASTM D638	
		Elongation %	Stress MPa (psi)	Elongation %	Stress MPa (psi)
105	70 (1.3)	4.5	50 (7,210)	193	35 (6,240)
105	NB	5	47 (6,900)	300	48 (7,000)
110	58 (1.1)	4	57 (8,200)	134	24 (3,500)
108	105 (1.9)	4.4	50 (7,200)	180	30 (4,300)
108	105 (1.9)	4.4	50 (7,200)	180	30 (4,300)
106	69 (1.3)	—	—	30	25 (3,600)
105	NB <sup>b</sup>	4	44 (6,300)	330	54 (7,800)
103	80 (1.5)	5	47 (6,900)	320	51 (7,400)
107	80 (1.5)	5	50 (7,200)	270	43 (6,300)
111	67 (1.2)	4	56 (8,100)	75	26 (3,800)
102	104 (1.9)	4.4	50 (7,210)	38	25 (3,600)
112	980 (18.4)	6	43 (6,200)	210	53 (7,700)
111	860 (16.1)	7	43 (6,200)	210	52 (7,500)
115	650 (12.2)	7	44 (6,400)	140	53 (7,700)



**Eastman Chemical Company  
Corporate Headquarters**

P.O. Box 431  
Kingsport, TN 37662-5280 U.S.A.

U.S.A. and Canada, 800-EASTMAN (800-327-8626)  
Other Locations, +(1) 423-229-2000

[www.eastman.com/locations](http://www.eastman.com/locations)

Although the information and recommendations set forth herein are presented in good faith, Eastman Chemical Company and its subsidiaries make no representations or warranties as to the completeness or accuracy thereof. You must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment, or formulation in conflict with any patent, and we make no representations or warranties, express or implied, that the use thereof will not infringe any patent. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Safety Data Sheets providing safety precautions that should be observed when handling and storing our products are available online or by request. You should obtain and review available material safety information before handling our products. If any materials mentioned are not our products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

© 2016 Eastman Chemical Company. Eastman brands referenced herein are trademarks of Eastman Chemical Company or one of its subsidiaries. The ® used on Eastman brands denotes registered trademark status in the U.S.; marks may also be registered internationally. Non-Eastman brands referenced herein are trademarks of their respective owners.