

Eastman **TETRASHIELD™**
protective resin systems

High performance
resins for
automotive OEM
clear coats

EASTMAN


Protection without compromise

Consumers want great-looking coatings that last, while original equipment manufacturers (OEMs) seek affordable performance. That means formulators must manage complex variables, especially in resin selection. Eastman Tetrashield™ protective resin systems help with both, adding distinctive performance and increasing formulation latitude in automotive clear coat systems.

Durable and tough, Tetrashield-containing clear coats enhance appearance, improve weatherability, and bolster scratch resistance. Lab tests show that coating formulations with Tetrashield offer significant durability and aesthetic enhancements compared to coatings using other resins.

Tetrashield polyester resins demonstrate performance that can't be achieved with traditional polyesters. This is due to the inclusion of 2,2,4,4-tetramethyl-1,3-cyclobutane diol (TMCD). The unique features of TMCD enable beneficial properties in clear coat formulations. For example, its tetramethyl configuration gives polyester resins excellent solubility, very good compatibility with other resins, and lower viscosity at higher applied coating solids. The shielded secondary hydroxyls within polyesters containing TMCD contribute to improved stain, chemical, and humidity resistance. The cycloaliphatic structure increases resin glass transition temperature (T_g) for improved hardness without significantly impacting flexibility. These characteristics offer formulators and OEMs a sustainable solution to strengthen their coatings portfolio.

Figure 1. TMCD glycol



In a world where the environment is tough on cars—and consumers are tough critics—protect what's important with Eastman Tetrashield™ protective resin systems.

For more information, visit [eastman.com/Tetrashield](https://www.eastman.com/Tetrashield).

Eastman Tetrashield™ protective resin systems for automotive OEM clear coat applications

Table 1. Physical properties

Tetrashield resin	AC1010	AC1020	AC1040 ^a	AC1041
Solvent	<i>n</i> -Butyl acetate	<i>n</i> -Butyl acetate	<i>n</i> -Butyl acetate	<i>n</i> -Butyl acetate
% Nonvolatiles	75	75	75	75
Acid number, mg KOH/g (determined on resin solids)	≤10	≤10	≤5	≤3
Hydroxyl number, mg KOH/g (determined on resin solids)	165	150	305	260
Viscosity, poise Brookfield DV-II, 25°C	30	65	220	230
Color, APHA	≤75	≤75	≤75	≤75

^aNot TSCA listed for use in North America

Table 2. Common uses and performance properties of clear coat formulations incorporating Tetrashield resins

Tetrashield resin ¹	1K	2K	Chemical resistance	Scratch resistance ²	Flexibility	Durability	Florida acid etch ³
AC1010	Highly recommended	Recommended	Recommended	Highly recommended	Recommended	Highly recommended	Recommended
AC1020	Recommended	Highly recommended	Highly recommended	Recommended	Recommended	Highly recommended	Recommended
AC1040	Highly recommended	Highly recommended	Highly recommended	Recommended	Recommended	Highly recommended	Recommended
AC1041	Highly recommended	Highly recommended	Highly recommended	Recommended	Recommended	Highly recommended	Recommended

Legend: ■ Recommended, ■ Highly recommended

¹Evaluated as a co-resin in an internal clear coat formulation; similar performance is also exhibited when 100% Tetrashield is used as a main binder ²As determined by microscratch ³Blount Island—Jacksonville, Fla., exposure

Tetrashield resins have been shown to enhance the performance of multiple clear coat technologies. Use level should be determined experimentally to ensure properties meet performance specifications.



Eastman Corporate Headquarters

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

U.S.A. and Canada, 800-EASTMAN (800-327-8626)
Other Locations, +(1) 423-229-2000

www.eastman.com/locations

Although the information and recommendations set forth herein are presented in good faith, Eastman Chemical Company ("Eastman") and its subsidiaries make no representations or warranties as to the completeness or accuracy thereof. You must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment, or formulation in conflict with any patent, and we make no representations or warranties, express or implied, that the use thereof will not infringe any patent. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Safety Data Sheets providing safety precautions that should be observed when handling and storing our products are available online or by request. You should obtain and review available material safety information before handling our products. If any materials mentioned are not our products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

© 2020 Eastman. Eastman brands referenced herein are trademarks of Eastman or one of its subsidiaries or are being used under license. The ® symbol denotes registered trademark status in the U.S.; marks may also be registered internationally. Non-Eastman brands referenced herein are trademarks of their respective owners.