

Eastman 168™ non-phthalate plasticizer with secondary plasticizers

Secondary plasticizers are typically aliphatic, aromatic, and naphthenic hydrocarbons used in plastisol applications. They generally have a lower cost compared to general-purpose plasticizers, which helps to optimize plastisol formulation cost. Secondary plasticizers are also used to adjust plastisol viscosity for proper processing of the material. However, many of these secondary plasticizers are not completely compatible in finished vinyl and cannot be used by themselves as the sole plasticizer. Incompatibility can be seen in the form of exudation and crease whitening.

Formulations and experimental data

The compatibility of secondary plasticizers in plastisols using Eastman 168™ non-phthalate plasticizer was investigated. Basic plastisol formulations containing Eastman 168, PVC resin, a heat stabilizer, and varying levels of secondary plasticizers were analyzed for compatibility. See Tables 1 and 2 for a description of the compositions used in these tests.

Table 1 Formulations

Formulation	Phr (parts per hundred resin)
Eastman 168™ non-phthalate plasticizer	60
Secondary plasticizer	5, 10, 15
Oxy™ 654 PVC dispersion resin, 71 K value	100
Akrostab™ LT 4798 (Ba/Zn) heat stabilizer	3

Table 2 Secondary plasticizers used in experiment

Secondary plasticizer	CAS #
Jayflex™ 210 (Naphthenic hydrocarbon)	64742-53-6
Jayflex™ 215 (Aliphatic hydrocarbon)	64771-82-8
Mineral spirits	—
Mineral seal oil	—
Epoxidized soybean oil	8013-07-8
Eastman TXIB™ formulation additive	6846-50-0
Cereclor™ S45 C14-17 chlorinated paraffin (45% chlorine)	085535-85-9
Cereclor™ S52 C14-17 chlorinated paraffin (52% chlorine)	085535-85-9
Viscobyk™ 4040 (Aliphatic hydrocarbons ^a)	—
Viscobyk™ 5050 (Low volatile carboxylic acid derivatives ^b)	—
Exxsol™ D80 (Dearomatized aliphatic hydrocarbon solvent ^c)	64742-47-8
Exxsol™ D95 (Dearomatized aliphatic hydrocarbon solvent ^d)	64742-47-9

^aWith neutral wetting and dispersing component ^b+ Acidic wetting and dispersing components

^cInitial BP 406°F, dry point 457°F ^dInitial BP 441°F, dry point 487°F

Plastisols were prepared in Hobart mixers using low shear paddles. Mixing time was 25 minutes, followed by deaeration of the plastisols. Vinyl sheets 0.07"-thick were fused in a convection oven for 20 minutes @ 375°F. Loop compatibility tests were performed from samples of each formulation. A small piece of vinyl from each 0.07"-thick sheet was bent and

held in position. The outside diameter of looped sample was 5/16". Looped samples were checked after one hour, one day, and one week for any sign of exudation by wiping the inside of the loop with cigarette paper. Conditioning and testing were performed in an ambient temperature laboratory.

The following ratings were given for the level of exudation observed:

0 = no exudation **1 = slight exudation** **2 = moderate exudation** **3 = heavy exudation**

Table 3 One hour compatibility

Secondary plasticizer	5 phr	10 phr	15 phr
Jayflex™ 210 (Naphthenic hydrocarbon)	0	0	0
Jayflex™ 215 (Aliphatic hydrocarbon)	1	2	3
Mineral spirits	0	0	0
Mineral seal oil	0	0	2
Epoxidized soybean oil	0	0	0
Eastman TXIB™ formulation additive	0	0	0
Cereclor™ S45 C14-17 chlorinated paraffin (45% chlorine)	0	0	0
Cereclor™ S52 C14-17 chlorinated paraffin (52% chlorine)	0	0	0
Viscobyk™ 4040 (Aliphatic hydrocarbons ^a)	0	0	0
Viscobyk™ 5050 (Low volatile carboxylic acid derivatives ^b)	1	1	2
Exxsol™ D80 (Dearomatized aliphatic hydrocarbon solvent ^c)	1	1	1
Exxsol™ D95 (Dearomatized aliphatic hydrocarbon solvent ^d)	1	1	1

^aWith neutral wetting and dispersing component ^b+ Acidic wetting and dispersing components

^cInitial BP 406°F, dry point 457°F ^dInitial BP 441°F, dry point 487°F

Table 4 One day compatibility

Secondary plasticizer	5 phr	10 phr	15 phr
Jayflex™ 210 (Naphthenic hydrocarbon)	0	0	1
Jayflex™ 215 (Aliphatic hydrocarbon)	2	3	3
Mineral spirits	0	0	0
Mineral seal oil	0	1	3
Epoxidized soybean oil	0	0	0
Eastman TXIB™ formulation additive	0	0	0
Cereclor™ S45 C14-17 chlorinated paraffin (45% chlorine)	0	0	1
Cereclor™ S52 C14-17 chlorinated paraffin (52% chlorine)	0	0	1
Viscobyk™ 4040 (Aliphatic hydrocarbons ^a)	0	1	1
Viscobyk™ 5050 (Low volatile carboxylic acid derivatives ^b)	1	1	2
Exxsol™ D80 (Dearomatized aliphatic hydrocarbon solvent ^c)	1	1	1
Exxsol™ D95 (Dearomatized aliphatic hydrocarbon solvent ^d)	2	2	2

^aWith neutral wetting and dispersing component ^b+ Acidic wetting and dispersing components

^cInitial BP 406°F, dry point 457°F ^dInitial BP 441°F, dry point 487°F

Table 5 One week compatibility

Secondary plasticizer	5 phr	10 phr	15 phr
Jayflex™ 210 (Naphthenic hydrocarbon)	0	0	1
Jayflex™ 215 (Aliphatic hydrocarbon)	2	3	3
Mineral spirits	0	0	0
Mineral seal oil	0	1	3
Epoxidized soybean oil	0	0	0
Eastman TXIB™ formulation additive	0	0	0
Cereclor™ S45 C14-17 chlorinated paraffin (45% chlorine)	0	0	2
Cereclor™ S52 C14-17 chlorinated paraffin (52% chlorine)	0	0	2
Viscobyk™ 4040 (Aliphatic hydrocarbons ^a)	1	1	2
Viscobyk™ 5050 (Low volatile carboxylic acid derivatives ^b)	1	2	2
Exxsol™ D80 (Dearomatized aliphatic hydrocarbon solvent ^c)	1	1	0*
Exxsol™ D95 (Dearomatized aliphatic hydrocarbon solvent ^d)	2	1	0*

*Exudate may have evaporated over the course of test period due to volatility of secondary.

^aWith neutral wetting and dispersing component ^b+ Acidic wetting and dispersing components

^cInitial BP 406°F, dry point 457°F ^dInitial BP 441°F, dry point 487°F

Conclusion

The secondary plasticizers used in this experiment have varying levels of compatibility in a plastisol containing Eastman 168™ non-phthalate plasticizer. This is dependent on the structure of the secondary and the level used. Highly aliphatic products are less compatible than aromatic and/or more polar products

when used in PVC plasticized with Eastman 168 non-phthalate plasticizer. Proper laboratory experimentation should be performed to determine the compatibility of secondary plasticizers with Eastman 168 in other formulations and with other secondary plasticizers not listed in Table 5.



**Eastman Chemical Company
Corporate Headquarters**

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

Telephone:
U.S.A. and Canada, 800-EASTMAN (800-327-8626)
Other Locations, (1) 423-229-2000
Fax: (1) 423-229-1193

Eastman Chemical Latin America

9155 South Dadeland Blvd.
Suite 1116
Miami, FL 33156 U.S.A.

Telephone: (1) 305-671-2800
Fax: (1) 305-671-2805

Eastman Chemical B.V.

Fascinatio Boulevard 602-614
2909 VA Capelle aan den IJssel
The Netherlands

Telephone: (31) 10 2402 111
Fax: (31) 10 2402 100

**Eastman (Shanghai) Chemical
Commercial Company, Ltd. Jingan Branch**

1206, CITIC Square
No. 1168 Nanjing Road (W)
Shanghai 200041, P.R. China

Telephone: (86) 21 6120-8700
Fax: (86) 21 5213-5255

Eastman Chemical Japan Ltd.

MetLife Aoyama Building 5F
2-11-16 Minami Aoyama
Minato-ku, Tokyo 107-0062 Japan

Telephone: (81) 3-3475-9510
Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House
3 Killiney Road
Singapore 239519

Telephone: (65) 6831-3100
Fax: (65) 6732-4930

www.eastman.com

Material Safety Data Sheets providing safety precautions that should be observed when handling and storing Eastman products are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Eastman, Eastman 168, and TXIB are trademarks of Eastman Chemical Company.

Akrostab is a trademark of Akcros Chemicals; Cereclor is a trademark of Ineos Chlor Limited; Exxsol and Jayflex are trademarks of ExxonMobil Chemical Company; Oxy is a trademark of OxyChem (Occidental Chemical Corporation); Viscobyk is a trademark of BYK-Chemie.

© Eastman Chemical Company, 2012.