

Formulação para esmalte—esmalte de efeito cromático/espelhado com butirato de acetato de celulose Eastman

Parte	Ingrediente/Nome INCI	Peso%	Nome do produto e fabricante sugerido
A	Butirato de acetato de celulose	70,1	CAB-381 20 (10%)/Eastman Chemical Company
B	Bentonita de estercalcônio	10,0	Tixogel-MPZ (7%)/BYK Chemie
C	Isobutirato de acetato de sacarose	0,7	SAIB 90 EA/Eastman Chemical Company
D	Pó de alumínio/acetato de etila	1,8	Metalure® A31017 (10% aluminum)/Eckart
E	Acetato de butila	17,4	Acetato de <i>n</i> -butila/Eastman Chemical Company*

Procedimento

1. Prepare a solução de 10% da parte A em 60:40 de acetato de etila: acetato de butila em um misturador de alto cisalhamento.
2. Prepare um pré-gel de 7% da parte B em 60:40 de acetato de etila: acetato de butila em um misturador de alto cisalhamento.
3. Misture as partes A, B e C juntas em um agitador de paletas.
4. Misture cuidadosamente a parte D nesta mistura usando agitação fraca para evitar a danificação dos flocos.
5. Dilua até a viscosidade da aplicação com a parte E.
6. Derrame a mistura em uma garrafa de esmalte.

**Confira com seu representante Eastman para disponibilidade em sua região.*





Eastman Corporate Headquarters

P.O. Box 431

Kingsport, TN 37662-5280 U.S.A.

U.S.A. and Canada, 800-EASTMAN (800-327-8626)

Other Locations, +(1) 423-229-2000

www.eastman.com/locations

Although the information and recommendations set forth herein are presented in good faith, Eastman Chemical Company ("Eastman") and its subsidiaries make no representations or warranties as to the completeness or accuracy thereof. You must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment, or formulation in conflict with any patent, and we make no representations or warranties, express or implied, that the use thereof will not infringe any patent. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Safety Data Sheets providing safety precautions that should be observed when handling and storing our products are available online or by request. You should obtain and review available material safety information before handling our products. If any materials mentioned are not our products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

© 2018 Eastman. Eastman brands referenced herein are trademarks of Eastman or one of its subsidiaries or are being used under license. The ® symbol denotes registered trademark status in the U.S.; marks may also be registered internationally. Non-Eastman brands referenced herein are trademarks of their respective owners.