



Eastman Coatings

Featured in the November 2004 issue of Paint & Coatings Industry, this is the third in a series of articles regarding the 'Nuts and Bolts' of formulating. The author, Kevin Williams, discusses factors affecting the performance of chlorinated polyolefin (CPO) adhesion promoters in coatings and common U.S. application testing methods.

Formulating Solutions: Getting the Most Out of Chlorinated Polyolefin (CPO) Adhesion Promoters

Chlorinated polyolefin (CPO) adhesion promoters are widely used as adhesion-promoting resins for coatings applied to plastic substrates, such as polypropylene (PP) and thermoplastic olefin (TPO). PP and TPO parts are used in automotive interior and exterior applications and are notoriously difficult to coat due to their low surface energy. This issue can be resolved by applying a CPO-based adhesion promoter to the plastic part before application of a coating (see Tables 1 and 2).

There are several factors that can affect the performance of a CPO-based adhesion promoter. Application parameters play a significant role in designing a system that will provide optimum adhesion performance. Of particular importance is the temperature at which a coating applied to a PP or TPO part is cured or baked. In addition, substrate and CPO composition can influence overall adhesion performance.

This article will highlight the effects of coating bake temperature and adhesion promoter composition on the performance properties of coated TPO. It will also detail test results, such as gasoline resistance and peel strength, demonstrating how the two factors can affect the performance of a CPO under real-life applications. This information can be used as a basis from which to utilize a CPO adhesion promoter to meet specific needs.

Factors Affecting Performance Coating Bake Temperature

Coating bake temperature is the temperature at which the coating applied to the TPO part is cured. Coating bake temperature can have an effect on the interaction between a CPO-based adhesion promoter and the surface of TPO, which can affect performance. For best results, coating adhesion is enhanced when the coated TPO parts are baked at temperatures over 100°C, given the same coating type. However, CPO-based adhesion promoters are successfully used in applications, such as automotive refinish applications, where the coating is air-dried or baked at temperatures lower than 100°C.

The chemical and physical properties of the CPO can also have a significant effect on adhesion performance. Addition of co-resins to CPO's can enhance adhesion, reduce blistering and improve the appearance of coatings applied over the adhesion promoter layer. CPO's have limited compatibility with most resin types, but unlike

conventional coatings this may not be detrimental to performance. CPO's promote adhesion best when they are at the interface of the substrate and the coating applied over the substrate. This means that a formulated adhesion promoter system with a CPO and borderline compatible co-resin may actually allow the CPO to reach the interface more readily. A number of co-resin types can be used with CPO, including acrylic, acrylic-modified alkyds, polyesters and others. The level of CPO used in the formulation will be dependent upon the substrate, coating type and required performance properties (see Table 2).

Table 1
CPO Adhesion Promoter

Component	Weight %
Eastman CP 730-1 (20% in Xylene)	25.0 g
Toluene	75.0 g
Total	100.0 g

Table 2
**CPO Adhesion Promoter with
Modified Alkyd Co-Resin**

Component	Weight %
Eastman CP 730-1 (20% in Xylene)	20.0 g
Macopol HS 1158 (70% in butyl acetate)*	22.9 g
Toluene	57.1 g
Total	100.0 g

*Supplied by Resolution Specialty Materials, Inc.

Application Tests

Gasoline Resistance

In automotive exteriors, coated TPO parts may be exposed to gasoline, depending on the location of the parts. Gasoline can permeate through the coating on a plastic part and find its way to the adhesion promoter layer, which can result in adhesion loss due to dissolution of the adhesion promoter. Coating bake temperature can have a significant effect on the gasoline-resistance properties of coated TPO's. Each substrate/adhesion promoter/coating system is different, but in general, gasoline resistance of coated TPO parts

improves with increasing bake temperature, given the same coating type. The chemical and physical properties of the CPO can also significantly affect gasoline resistance performance.

Peel Strength

Peel strength is a test method used to measure the amount of force required to peel a coating system away from the substrate to which it is applied. This can be accomplished by imbedding a mesh polyester fabric into the coating system before it has been cured and then curing the coating system. The fabric can then be attached to a tensile tester to measure peel strength of the substrate/adhesion promoter/coating system.

Substrate type, adhesion promoter composition, coating type and coating bake temperature can have a significant effect on the peel strength properties of coated TPO substrates. Once again, increasing bake temperature often results in higher peel strengths, given the same coating type. CPO chemical and physical properties and the overall adhesion promoter formulation composition can significantly affect peel strength results. For formulated adhesion promoter systems, the right type and level of CPO must be used to obtain sufficient peel strength properties.



Formulating Solutions: Getting the Most Out of Chlorinated Polyolefin (CPO) Adhesion Promoters

About Eastman's Coatings Business

For more than 70 years, Eastman has been a leading provider of high-quality raw materials and services for the global paint and coatings industry. Today, Eastman provides a comprehensive portfolio of solvents, coalescents, cellulose esters, adhesion promoters and resin intermediates used in conventional, high-solids, waterborne and powder coatings for architectural, automotive and industrial applications.

With its in-depth understanding of the coatings market and technology-based innovation, Eastman is helping customers meet the demands of a dynamic regulatory environment and deliver value creating solutions to the changing market needs. In providing world-class technical service, Eastman demonstrates its commitment to helping its customers deliver the most cost-effective solutions to meet the challenging performance and environmental requirements in today's marketplace.

Eastman Chemical Company Corporate Headquarters

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

Telephone:
U.S.A. and Canada, 800-EASTMAN (800-327-8626)
Other Locations, (1) 423-229-2000
Fax: (1) 423-229-1193
www.eastman.com

Material Safety Data Sheets providing safety precautions, that should be observed when handling and storing Eastman products, are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Eastman is a trademark of Eastman Chemical Company.

© Eastman Chemical Company, 2005.

Publication GN-471
March 2005

EASTMAN