

# Eastman SPECIALTY KETONES

Eastman™ specialty ketones can help achieve high-solids coatings with excellent appearance and performance. One of the most prevalent drivers in many applications today, and especially in coatings, is the need to meet volatile organic content (VOC) regulations.



Often, this requires a change to higher-solids coating systems which contain less solvents. It can be difficult to achieve the required balance of VOC content, application properties, appearance, and performance. While such high-solids systems may offer higher resin content for better coverage and protection, these high-solid

systems may also have higher viscosity profiles which can lead to poor application and appearance properties.

## High solvency and low density

Ketones are known to have excellent solvent activity with a wide range of different resin systems. The high-solvency characteristics along with low density make ketones the perfect solvent for high-solids coatings. As shown in Table 1, their high solvency allows ketones to lower the viscosities of

various resin systems better than any other solvent with comparable evaporation rates. The low density of the ketones yields coatings containing fewer grams of solvent per liter of coating (lower VOC) when compared to solvents with the same evaporation rate.

## Evaporation rate

Eastman provides ketones with a wide range of evaporation rates. This allows formulators to tailor their solvent blend to give their coatings the required drying profile for all types of systems. Depending on the application and climatic conditions, the solvent blend can be adjusted to either increase or decrease evaporation rate to improve the paint appearance. Eastman™ specialty ketones can be used to achieve excellent flow and leveling and sag resistance, while preventing defects such as solvent popping and dry spray.

## Surface tension

The surface tension of coatings usually increases as the solids content increases. This high surface tension can contribute to poor sprayability, insufficient wetting of the substrate, cratering, and picture framing. Selecting a solvent blend with the proper surface tension aids in balancing activity to reduce such defects.

Pound for pound, Eastman™ specialty ketones offer more benefits than any solvent available.

**Table 1: Comparison of solvent properties**

Solvent	Evaporation Rate (n-BuOAc = 1)	R ½-s NC Viscosity 8% Solids	Eastman™ CAB-381-0.5 Viscosity 8% Solids	Solvent Density, g/cm³	Surface Tension Dynes/cm
Methyl Propyl Ketone (Eastman™ MPK)	2.3	14	13	0.81	26.6
n-Propyl Acetate		22	18	0.89	24.3
Methyl Isoamyl Ketone (Eastman™ MIAK)	0.5	23	20	0.81	25.8
Methyl Amyl Acetate		54	N/A	0.97	22.6
n-Butyl Propionate		109	116	0.87	25.3
Methyl Amyl Ketone (Eastman™ MAK)	0.4	25	20	0.82	26.1
PM Acetate		64	43	0.97	26.4
p-Amyl Acetate		40	31	0.87	28.5
IBIB		100	Insoluble	0.86	23.2



Eastman Chemical Company is committed to being its customers' strategic partner of choice, developing and delivering differentiated solutions that meet and anticipate their needs.

N O R T H A M E R I C A N E D I T I O N

## EASTMAN

### **Eastman Chemical Company Corporate Headquarters**

P.O. Box 431  
Kingsport, TN 37662-5280 U.S.A.  
Telephone:  
U.S.A. and Canada, 800-EASTMAN  
(800-327-8626)  
Other Locations, (1) 423-229-2000  
Fax: (1) 423-229-1193

### **Eastman Chemical Latin America**

9155 South Dadeland Blvd.  
Suite 1116  
Miami, FL 33156 U.S.A.  
Telephone: (1) 305-671-2800  
Fax: (1) 305-671-2805

### **Eastman Chemical B.V.**

Fascinatio Boulevard 602-614  
2909 VA Capelle aan den IJssel  
The Netherlands  
Telephone: (31) 10 2402 111  
Fax: (31) 10 2402 100

### **Eastman (Shanghai) Chemical Commercial Company, Ltd. Jingan Branch**

1206, CITIC Square  
No. 1168 Nanjing Road (W)  
Shanghai 200041, P.R. China  
Telephone: (86) 21 6120-8700  
Fax: (86) 21 5213-5255

### **Eastman Chemical Japan, Ltd.**

AIG Aoyama Building 5F  
2-11-16 Minami Aoyama  
Minato-ku, Tokyo 107-0062 Japan  
Telephone: (81) 3-3475-9510  
Fax: (81) 3-3475-9515

### **Eastman Chemical Asia Pacific Pte. Ltd.**

#05-04 Winsland House  
3 Killiney Road  
Singapore 239519  
Telephone: (65) 6831-3100  
Fax: (65) 6732-4930

**[www.eastman.com](http://www.eastman.com)**

Material Safety Data Sheets providing safety precautions, that should be observed when handling and storing Eastman products, are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

*Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.*

Eastman is a trademark of Eastman Chemical Company.

© Eastman Chemical Company, 2008.

M-337B 5/08  
Printed in U.S.A.