

# Appliance materials **selector guide**

*Specialty plastics for the appliance  
and floor care markets*



# Appliance materials selector guide

Product	Description	Suggested applications	Specific gravity ASTM D792	Tensile yield ASTM D638		Tensile break ASTM D638	
				Elongation %	Stress MPa (psi)	Elongation %	Stress MPa (psi)
<b>DuraStar™ polymers</b>							
DS1010 clear and tints	PCTA	<ul style="list-style-type: none"> <li>• Refrigerator interior parts</li> <li>• Floor care</li> <li>• Washing machine lids</li> </ul>	1.20	5	47 (6,900)	300	51 (7,400)
DS2010 clear and tints			1.20	5	46 (6,700)	310	53 (7,700)
DS1910HF clear and tints			1.19	5	50 (7,200)	270	43 (6,300)
<b>Eastar™ copolyesters</b>							
DN011 clear	PCTG	<ul style="list-style-type: none"> <li>• Refrigerator interior parts</li> <li>• Floor care</li> </ul>	1.23	4	44 (6,300)	330	54 (7,800)
EN067 clear and tints	PET		1.32	4	57 (8,200)	134	24 (3,500)
GN007 clear and tints	PETG		1.27	4.4	50 (7,200)	180	30 (4,300)
<b>Tenite™ cellulosics</b>							
Propionate 375-12—12% PZ clear and tints	Cellulose acetate propionate	• Floor care	1.20	45	31.7 (4,600)	45	31 (4,800)
<b>Eastman Tritan™ copolyesters</b>							
TX 1001 (clear and opaque)	Copolyester	<ul style="list-style-type: none"> <li>• Small appliances</li> <li>• Dryer doors</li> <li>• Floor care</li> </ul>	1.18	6	43 (6,200)	210	53 (7,700)
TX 1501 HF (clear and opaque)			1.18	7	43 (6,200)	210	52 (7,500)
TX 2001 (clear and opaque)			1.17	7	44 (6,400)	140	53 (7,700)

Product	Flexural modulus MPa (10 <sup>5</sup> psi) ASTM D790	Izod impact notched J/m (ft.lbf/in.) @ 23°C (73°F) ASTM D256	Deflection temperature °C (°F) ASTM D648		Optical properties ASTM D1003	
			@ 1.82 MPa (264 psi)	@ 0.455 MPa (66 psi)	Transmittance %	Haze %
<b>DuraStar™ polymers</b>						
DS1010 clear and tints	2,000 (2.9)	80 (1.5)	65 (149)	75 (167)	91	0.3
DS2010 clear and tints	1,900 (2.8)	370 (7.0)	65 (149)	73 (164)	91	0.3
DS1910HF clear and tints	1,900 (2.7)	80 (1.5)	66 (150)	73 (163)	92	<1
<b>Eastar™ copolyesters</b>						
DN011 clear	1,800 (2.6)	NB*	64 (147)	73 (163)	92	<0.1
EN067 clear and tints	2,600 (3.8)	58 (1.1)	61 (142)	66 (151)	84	—
GN007 clear and tints	2,100 (3.0)	105 (1.9)	62 (143)	70 (158)	90	0.2
<b>Tenite™ cellulosics</b>						
Propionate 375-12—12% PZ clear and tints	1,448 (2.1)	416 (7.8)	75 (167)	83 (181)	<90	<8
<b>Eastman Tritan™ copolyesters</b>						
TX 1001 (clear and opaque)	1,550 (2.3)	980 (18.4)	85 (185)	99 (210)	90	<1
TX 1501 HF (clear and opaque)	1,575 (2.3)	860 (16.1)	81 (178)	94 (201)	91	<1
TX 2001 (clear and opaque)	1,585 (2.3)	650 (12.2)	92 (198)	109 (228)	92	<1

\*Nonbreak as defined by ASTM D256 using 3.2-mm (1/8-in.) specimens.

Unless noted otherwise, all tests are run @ 23°C (73°F) and 50% relative humidity. Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Conversions of metric/U.S. customary values may have been rounded off and therefore may not be exact conversions.



**Eastman Corporate Headquarters**  
P.O. Box 431  
Kingsport, TN 37662-5280 U.S.A.

U.S.A. and Canada, 800-EASTMAN (800-327-8626)  
Other Locations, +(1) 423-229-2000

[www.eastman.com/locations](http://www.eastman.com/locations)

Although the information and recommendations set forth herein are presented in good faith, Eastman Chemical Company ("Eastman") and its subsidiaries make no representations or warranties as to the completeness or accuracy thereof. You must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment, or formulation in conflict with any patent, and we make no representations or warranties, express or implied, that the use thereof will not infringe any patent. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Safety Data Sheets providing safety precautions that should be observed when handling and storing our products are available online or by request. You should obtain and review available material safety information before handling our products. If any materials mentioned are not our products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

© 2017 Eastman. Eastman brands referenced herein are trademarks of Eastman or one of its subsidiaries or are being used under license. The ® symbol denotes registered trademark status in the U.S.; marks may also be registered internationally. Non-Eastman brands referenced herein are trademarks of their respective owners.