

Solvent substitution or replacement options for MIBK

Methyl isobutyl ketone (MIBK) is a familiar solvent to the coatings industry. Due to its solvency properties and its medium evaporation rate, it finds its way into many coatings applications. While MIBK offers excellent performance and versatility, some agencies have expressed health concerns with this solvent. For example, MIBK is listed as a hazardous air pollutant (HAP) according to Title III of the Clean Air Act Amendments of 1990.

More recently, a new concern has been brought to light by the International Agency for Research on Cancer (IARC, a subgroup of the World Health Organization). The IARC has recently reviewed all the available toxicological data on MIBK and have announced that they intend to classify MIBK as Group 2B, possibly carcinogenic to humans.

In response to this intent by IARC, the California Environmental Protection Agency's Office of Environmental Health Hazard Assessment (OEHHA) has announced that they intend to list MIBK under Proposition 65, the Safe Drinking Water and Toxic Enforcement Act of 1986, as "known to the state to cause cancer or reproductive harm."

The purpose of this technical brief is to inform our customers of the recent intent by the IARC to classify MIBK as a Group 2B carcinogen and the intent by OEHHA to place MIBK on the Proposition 65 list. It is also intended to provide alternative solvent options for substituting or replacing MIBK.

Solvent requirements are usually specific, and they vary from application to application. Because of this, it is not very common for a solvent to be replaced with a single other solvent without making some adjustments to the formulation and/or the process. Sometimes, a more viable option is to substitute with a blend of solvents.

Blending solvents is a good approach because it allows formulators to dial in a specific evaporation profile and solvency to match the performance of the solvent they are looking to replace. This could allow formulators to make a substitution without making further adjustments to the paint formula. Table 1 shows 3 different solvent blends that should provide similar performance to MIBK.

Table 1 Solvent blends

	Control wt%	Blend #1 wt%	Blend #2 wt%	Blend #3 wt%
Solvent				
Methyl isobutyl ketone	100	–	–	–
Methyl propyl ketone	–	80	50	30
Methyl isoamyl ketone	–	20	25	–
Methyl acetate	–	–	25	–
Isobutyl acetate	–	–	–	70
Relative evaporation rate (RER), nBuOAc = 1				
	1.6	1.6	1.6	1.6
Hansen solubility parameters				
Dispersion	7.5	7.8	7.7	7.5
Polar	3.0	3.5	3.4	2.4
Hydrogen bonding	2.0	2.2	2.5	2.8
Total	8.3	8.8	8.8	8.4

These solvents were selected based on their properties and their performance reducing various coatings resins. Tables 2 and 3 contain select solvent properties and Brookfield viscosities with different resins. For more solvent properties, refer to the Solvent Selector Chart, Eastman publication M-167. For more resin solubility information, refer to the Resin Solubility Chart, Eastman publication M-282C (www.eastman.com or contact 800-EASTMAN).

While current market conditions are commanding an unusually high price per lb for MIBK, the blends proposed in this brief would more than likely be lower cost alternatives. Table 4 compares the benefits of the 3 different blends and their relative cost difference to MIBK based on the current market.

Table 2 Solvent properties

Solvent	RER, nBuOAc = 1	Density, lb/gal	Water solubility, wt% (in water/water in) @ 20°C	Electrical resistance, megohms
Eastman™ methyl acetate	6	7.8	22.0/7.3	0.4
Eastman™ MPK	2.3	6.74	3.1/4.2	0.3
Eastman™ MIBK	1.6	6.67	2.0/1.0	0.4
Eastman™ isobutyl acetate	1.4	7.25	0.7/1.6	>20
Eastman™ MIAK	0.5	6.76	0.5/1.2	0.6

Table 3 Resin solubility—Brookfield viscosities

Solvent	Acrylic PARALOID™ B-66 (40 wt%)	Cellulose acetate butyrate CAB-381-0.5 (8 wt%)	Epoxy EPON™ 1001 (50 wt%)	Isocyanate Desmodur™ N 100 (50 wt%)	Polyester POLYMAC™ 057-5776 (65 wt%)	Vinyl acetate AYAA (20 wt%)
Eastman™ MIBK	390	15	68	9	105	45
Eastman™ methyl acetate	340	14	40	7	57	45
Eastman™ MPK	240	13	40	8	71	38
Eastman™ isobutyl acetate	1200	28	110	12	145	65
Eastman™ MIAK	650	20	90	11	85	50

Table 4 Benefit and cost comparison

	Benefit	Cost relative to current MIBK list price*
Blend #1	Performance	Lower
Blend #2	25% lower VOC	Lower
Blend #3	Most economical	Lower

*Based on current market conditions and subject to change



**Eastman Chemical Company
Corporate Headquarters**

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

Telephone:
U.S.A. and Canada, 800-EASTMAN (800-327-8626)
Other Locations, (1) 423-229-2000
Fax: (1) 423-229-1193

Eastman Chemical Latin America

9155 South Dadeland Blvd.
Suite 1116
Miami, FL 33156 U.S.A.

Telephone: (1) 305-671-2800
Fax: (1) 305-671-2805

Eastman Chemical B.V.

Fascinatio Boulevard 602-614
2909 VA Capelle aan den IJssel
The Netherlands

Telephone: (31) 10 2402 111
Fax: (31) 10 2402 100

**Eastman (Shanghai) Chemical
Commercial Company, Ltd. Jingan Branch**

1206, CITIC Square
No. 1168 Nanjing Road (W)
Shanghai 200041, P.R. China

Telephone: (86) 21 6120-8700
Fax: (86) 21 5213-5255

Eastman Chemical Japan Ltd.

MetLife Aoyama Building 5F
2-11-16 Minami Aoyama
Minato-ku, Tokyo 107-0062 Japan

Telephone: (81) 3-3475-9510
Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House
3 Killiney Road
Singapore 239519

Telephone: (65) 6831-3100
Fax: (65) 6732-4930

www.eastman.com

Material Safety Data Sheets providing safety precautions that should be observed when handling and storing Eastman products are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

Eastman is a trademark of Eastman Chemical Company.

Desmodur is a trademark of Bayer Material Science LLC; EPON is a trademark of Momentive Specialty Chemicals Inc.; PARALOID is a trademark of The Dow Chemical Company or an affiliated company of Dow; Polymac is a trademark of PCCR, USA.

© Eastman Chemical Company, 2011.