

**SALES SPECIFICATIONS**

Sales Specification No : 11126-10  
Effective Date : 01/22/2010  
Page No. 1 of 1

**EASTMAN****PRODUCT NAME****Eastman(TM) Cellulose Acetate Butyrate (CAB-381-2 BP)****SPECIFICATIONS**

PROPERTY	LIMITS	TEST METHOD
Acetyl, W%	13 - 16	TECE-A-CL-G-GC-29
Butyryl, W%	33 - 38	TECE-A-CL-G-GC-29
Free Acidity by IC, PPM	300 MAX	TECE-A-CL-G-IC-5
Moisture, wt%	3.0 MAX	TECE-A-CL-G-GA-55
Hydroxyl, W%	1.5 - 2.1	TECE-A-CL-G-POT-27
ASTM-A Viscosity, sec	1.9 - 2.5	TECE-A-CL-G-V-3

Eastman Chemical Company · P.O. BOX 511 · Kingsport, Tennessee 37662 USA · 1-800-EASTMAN · 1-423-229-2000 · [www.EASTMAN.com](http://www.EASTMAN.com)

Sales Specification available on [Eastman.com](http://Eastman.com)

For reasons of safety and accuracy, the person performing this procedure must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers. Limits in this specification are applicable only to data obtained by the referenced test method.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the seller's conditions of sale.