

SALES SPECIFICATION

EASTMAN

Specification No: Plastolyn 290-0

Effective Date: 6/6/2002

Page 1 of 1

PRODUCT NAME

Plastolyn™ 290

SPECIFICATIONS

PROPERTY	LIMITS	TEST METHOD
Softening Point, Ring & Ball, °C	137 – 143	CASPI-A-AN-G-PP-085
Color (Gardner)	1 Max	CASPI-A-AN-G-AC-100

References:

06/06/02: Updated Jefferson Site Sales Specification to Eastman Chemical Company.

NOTE: This product was formerly known as Herculite® 290.

NOTE: Shelf Life is a guide not an absolute value. The product should be reanalyzed for critical properties at the end of its shelf life to see if it meets specification for use.

Recommended Shelf Life – **1095** Days (Flake – pastilles) from Date of Manufacture

Brand Name(s)™ is a trademark of Eastman Chemical Company.

Eastman Chemical Company · P.O. Box 511 · Kingsport, Tennessee 37662 USA · 1-800-EASTMAN · 1-423-229-2000 · www.EASTMAN.com

For reasons of safety and accuracy, the person performing this procedure must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers. Limits in this specification are applicable only to data obtained by the referenced test method.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product; and nothing herein waives any of the seller's conditions of sale.